

EE 型磁芯
EE CORES




Fig.1




Fig.2




Fig.3




Fig.4

規格 (Type)	尺寸(Unit: mm)						圖形	磁芯參數				單重 (g/set)	Al-value (nH/N ²)											
	A	B	C	D	E	F		C1 (mm ⁻¹)	Le (mm)	Ae (mm ²)	Ve (mm ³)		KP40	KP44	KP44L	KP50	KP95	KP96	KP97	KA50	KA70	KA100	KA120	
EE05/05	5.25±0.15	5.30±0.15	1.95±0.10	4.00±0.20	1.35±0.10	4.00±0.20	Fig.1	5.02	12.7	2.53	32.13	0.16				270	260	320	310	310	370	400		
EE08/08	8.30±0.20	8.00±0.20	3.90±0.15	6.00+0.30-0.00	2.00+0.00-0.30	6.00±0.20	Fig.1	2.36	19.2	8.15	156.48	0.76	800	800	800	760	970	920	920	1170	1500			
EE08/08A	8.30±0.25	8.00±0.20	2.00±0.15	6.00min	2.00+0.00-0.30	6.00±0.20	Fig.1	4.85	19.4	4.00	77.60	0.40	330		330	310	390	370	370					
EE08/08L	8.30±0.20	8.20±0.20	3.90±0.15	6.00+0.30-0.00	2.00+0.00-0.30	6.20±0.20	Fig.1	2.36	19.2	8.15	156.48	0.78	800	800	800	760	970	920	920	1170	1500			
EE08/8.2B	8.30±0.20	8.20±0.20	3.60±0.15	6.00+0.30-0.00	2.00+0.00-0.30	6.20±0.20	Fig.1	2.77	19.8	7.15	141.57	0.70	740	740	740	700	900	860	860					
EE8.6/8.6	8.60±0.20	8.60±0.20	3.80±0.20	6.50±0.20	2.10+0.00-0.30	6.40±0.20	Fig.1	2.54	20.6	8.10	166.86	0.82	780	780	780	740	960	900	900	1200	1560			
EE10/10	10.30±0.20	10.20±0.20	2.80±0.20	7.70min	2.30±0.20	7.90±0.20	Fig.1	3.83	25.0	6.53	163.25	0.81	410		470	440	560	530	530					
EE10/11	10.20+0.30-0.10	11.00+0.30-0.20	4.90+0.00-0.30	7.70min	2.40±0.20	8.60+0.30-0.20	Fig.1	2.33	26.6	11.4	303.24	1.50	850	890	890	840	1100	1030	1030	1400	1630			
EE10/11A	10.30±0.20	11.00+0.30-0.20	2.70±0.15	7.90±0.20	2.40±0.20	8.60+0.30-0.20	Fig.1	4.10	26.6	6.48	172.37	0.86		510	510	480	620	580	580		1100			
EE11.7	11.70±0.20	23.60±0.40	2.05+0.05-0.1	7.30±0.15	4.40±0.10	19.20±0.40	Fig.1	5.42	48.2	8.90	428.98	2.14	374		410	380	520	480	480					
EE12/06	12.00±0.25	6.40±0.30	6.50±0.20	8.90±0.25	3.10±0.15	3.60±0.30	Fig.1	0.917	17.6	19.2	337.92	1.74	180		1700	1620	2000	1910	1910					
EE13/11	12.70±0.25	11.40±0.26	3.18±0.13	9.50±0.25	3.20±0.13	8.20±0.26	Fig.1	2.72	27.7	10.2	282.85	1.40	800	830	830	780	830	790	790	1360	1650			
EE13/12	13.10±0.20	12.00±0.30	5.90±0.20	10.20min	2.80+0.00-0.40	9.20±0.20	Fig.1	1.89	30.3	16.0	484.80	2.40	1040	1040	1040	980	1240	1170	1170	1750	2000			
EE13/12B	13.00±0.30	12.00±0.30	6.20±0.20	9.90min	2.80+0.00-0.40	9.20±0.20	Fig.1	1.80	30.3	16.8	509.04	2.50	1080		1100	1040	1300	1230	1230					
EE13/12C	13.10±0.20	12.00±0.30	9.90±0.20	10.20min	2.80+0.00-0.40	9.20+0.30-0.10	Fig.1	1.13	30.3	26.8	812.04	4.00	1740		1700	1600	2100	1990	1990					
EE13/12E	13.00±0.30	12.40±0.20	6.00±0.20	10.50min	2.60±0.15	10.00±0.30	Fig.1	2.22	31.8	14.3	454.74	2.40	910		940	880	1150	1080	1080					
EE13/12F	13.10±0.20	12.00±0.30	2.95±0.30	10.20min	2.80+0.00-0.40	9.20+0.30-0.10	Fig.1	3.79	30.3	8.00	242.40	1.20	570		510	480	620	580	580					
EE13/12K	13.10±0.20	12.20±0.30	6.10±0.20	10.20min	2.80+0.00-0.40	9.50±0.20	Fig.1	1.94	31.1	16.0	496.80	2.45	1200		1250	1160	1560	1450	1450	2000				
EE13/12.4K	13.10±0.20	12.40±0.20	6.10±0.20	10.20min	2.80+0.00-0.40	9.70±0.20	Fig.1	1.97	31.5	16.0	504.00	2.50	1200		1250	1160	1560	1450	1450	2000				
EE13/12L	13.10±0.20	12.20±0.30	5.90±0.20	10.20min	2.80+0.00-0.40	9.50±0.20	Fig.1	1.89	30.3	16.0	484.80	2.40	1040	1040	1040	980	1250	1180	1180	1750	2000			
EE13/12M	13.00±0.30	12.20±0.30	6.10+0.1/-0.3	10.20min	2.80+0.00-0.40	9.50±0.20	Fig.1	1.91	30.5	16.0	488.00	2.46	1100	1140	1140	1070	1420	1330	1330					
EE13/13	12.6+0.5-0.4	13.0+0.0-0.4	3.7+0.0-0.3	8.90 min	3.7+0.0-0.3	9.0+0.6-0.0	Fig.1	2.40	29.7	12.4	368.28	1.82	780	810	810	760	980	830	830	1350	1590			
EE13.5/7.8	13.50±0.30	7.80±0.20	23.80±0.35	9.90min	3.00±0.20	5.10+0.30/-0.20	Fig.3	0.31	21.9	69.6	1524.24	8.04	6000		6000	5660	7200	6830	6830					
EE13.6/13	13.6+0.20/-0.25	13.00±0.30	3.65±0.15	10.00+0.20/-0.25	3.70±0.10	9.20±0.30	Fig.1	2.26	30.5	13.5	411.75	2.00			1000	940	1260	1180	1180					
EE14/7.5	14.00±0.30	7.50±0.20	14.00±0.25	11.00±0.30	3.00±0.15	4.50±0.30	Fig.1	0.517	21.7	42.0	911.40	4.65			3500	3320	4200	3990	3990					
EE15/07	15.00±0.30	7.00±0.30	10.20+0.20-0.40	11.70min	3.15±0.15	4.80±0.30	Fig.1	0.856	22.1	25.8	569.66	3.06	2230	2320	2320	2190	2400	2280	2280	3790	4900			
EE15/11.3	15.00±0.30	11.30±0.20	8.00±0.20	10.80±0.30	4.55±0.15	6.90±0.30	Fig.1	0.769	26.9	35.0	941.50	4.80			2400	2290	2900	2750	2750					
EE15.2/14	15.60±0.40	14.00±0.40	10.00±0.30	11.90±0.30	3.50±0.20	10.40±0.40	Fig.1	0.969	34.5	35.6	1228.20	6.30	2090	2090	2100	1980	2600	2450	2450					
EE16/10	16.00±0.30	8.80±0.20	10.00+0.20-0.40	11.70min	4.15±0.15	4.80±0.20	Fig.1	0.589	23.8	40.4	960.71	4.90	2800	2920	2920	2770	3600	3420	3420	4800	6000			
EE16/14	16.00±0.30	14.40±0.30	4.80±0.20	11.70min	4.00±0.20	10.40±0.30	Fig.1	1.92	35.5	18.5	656.75	3.38	1150	1200	1200	1120	1650	1530	1530	2090	2700			
EE16/14.6	16.00±0.30	14.60±0.30	4.80±0.20	11.70min	4.00±0.20	10.60±0.30	Fig.1	1.94	35.9	18.5	664.15	3.42	1150	1200	1200	1120	1650	1530	1530					
EE16/14.8	16.00±0.30	14.80±0.30	4.80±0.20	11.70min	4.00±0.20	10.80±0.30	Fig.1	1.95	36.1	18.5	667.85	3.45	1150	1200	1200	1120	1650	1530	1530					
EE16/14A	16.00±0.30	14.30±0.30	6.80±0.20	12.50min	3.18±0.18	11.00±0.30	Fig.1	1.68	36.7	21.9	803.73	4.00	1300	1350	1350	1260	1520	1430	1430	2400	3120			
EE16/14C	16.00±0.30	14.40±0.30	10.00±0.20	11.70min	4.00±0.20	10.40±0.30	Fig.1	0.878	35.1	40.0	1404.00	7.00	2300	2400	2400	2250	2900	2730	2730					
EE16/14D	16.00±0.30	14.40±0.30	4.40±0.20	11.70min	4.00±0.20	10.40±0.30	Fig.1	1.99	35.1	17.6	617.76	3.10		1020	1150	1070	1300	1220	1220					
EE16/14.6C	16.00±0.30	14.60±0.30	10.00±0.20	11.70min	4.00±0.20	10.60±0.30	Fig.1	0.888	35.5	40.0	1420.00	7.15	2300	2400	2400	2250	2830	2670	2670					
EE16/25	16.00±0.40	24.40±0.40	4.80±0.20	12.00±0.30	4.00±0.20	20.40±0.30	Fig.1	2.80	55.2	19.7	1087.44	5.30	780	780	810	760	1000	930	930	1590	1980			
EE16/25A	16.00±0.40	24.40±0.40	7.50±0.20	12.00±0.30	4.00±0.20	20.40±0.30	Fig.1	1.84	55.2	30.0	1656.00	8.10	1050		1300	1210	1600	1490	1490					

EE 型磁芯
EE CORES




Fig.1




Fig.2




Fig.3




Fig.4

規格 (Type)	尺寸(Unit: mm)						圖形	磁芯參數				單重 (g/set)	Al-value (nH/N ²)											
	A	B	C	D	E	F		C1 (mm ⁻¹)	Le (mm)	Ae (mm ²)	Ve (mm ³)													
													KP40	KP44	KP44L	KP50	KP95	KP96	KP97	KA50	KA70	KA100	KA120	
EE18/08	18.00±0.40	8.60±0.40	10.00±0.20	14.00±0.30	4.00±0.20	4.60±0.30	Fig.1	0.498	20.3	40.8	828.24	5.00	3100	3100	3100	2960	3900	3720	3720					
EE19/16	19.10±0.30	16.05±0.30	4.85±0.25	14.20min	4.85±0.25	11.45±0.25	Fig.1	1.68	39.2	23.3	913.36	4.50	1240	1300	1300	1220	1780	1660	1660	2240	3000			
EE19/16A	19.00±0.30	16.20±0.30	4.85±0.25	14.20min	4.60±0.30	11.20±0.30	Fig.1	1.68	39.2	23.3	913.36	4.50	1250	1300	1300	1220	1790	1670	1670	2250	3000			
EE19/16B	19.10±0.30	15.90±0.30	10.0±0.25	14.50±0.30	4.85±0.25	11.30±0.30	Fig.1	0.817	39.2	48.0	1881.60	9.30	2500		2600	2440	3200	3010	3010					
EE19/16C	19.10±0.30	16.05±0.30	7.60±0.20	14.50±0.30	4.85±0.25	11.45±0.30	Fig.1	1.10	39.2	35.5	1391.60	7.00	1850	1930	1930	181	2400	2250	2250					
EE19/16D	19.10±0.30	15.90±0.30	4.85±0.25	14.30min	4.85±0.25	11.30±0.30	Fig.1	1.68	39.2	23.3	913.36	4.50	1300		1300	1220	1600	1500	1500					
EE19/16E	19.30±0.30	16.00±0.30-0.50	7.00±0-0.40	14.10±0.60-0	5.10±0-0.50	11.30±0.30	Fig.1	1.22	39.6	32.5	1287.00	6.30	1720		1700	1600	2100	1980	1980					
EE19/16F	19.10±0.30	16.05±0.30	9.70±0.20-0.35	14.50±0.30	4.85±0.25	11.45±0.30	Fig.1	0.877	39.8	45.4	1806.92	9.06	2340	2340	2450	2300	2450	2330	2330					
EE19/16H	19.00±0.30	16.20±0.30	7.95±0.20	14.20min	4.60±0.30	11.20±0.30	Fig.1	1.06	39.7	37.3	1480.81	7.50	2000		2000	1880	2500	2350	2350					
EE19/16J	19.10±0.30	16.05±0.30	5.10±0.25	14.20min	4.85±0.25	11.45±0.30	Fig.1	1.67	39.9	23.9	953.61	4.80	1250		1300	1220	1600	1500	1500					
EE19/16K	19.10±0.30	16.05±0.3	9.50±0.20	14.20min	4.85±0.25	11.45±0.30	Fig.1	0.896	39.8	44.4	1767.12	8.90			2300	2160	3160	2960	2960					
EE19/16L	19.10±0.30	16.40±0.30	4.85±0.25	14.20min	4.85±0.25	11.80±0.30	Fig.1	1.68	39.2	23.3	913.36	4.62	1240		1300	1220	1600	1500	1500					
EE19/16.2M	19.10±0.30	16.20±0.30	5.20±0.20	14.20min	4.85±0.25	11.60±0.25	Fig.1	1.65	40.2	24.3	976.86	4.90			1330	1250	1630	1530	1530					
EE19/16N	19.10±0.30	16.05±0.30	13.00±0.25	14.50±0.30	4.85±0.25	11.45±0.25	Fig.1	0.65	39.8	60.8	2419.84	12.20	3700		3700	3380	4600	4300	4300					
EE19/16.4A	19.00±0.30	16.40±0.30	4.85±0.25	14.20min	4.60±0.30	11.40±0.30	Fig.1	1.77	40.1	22.7	910.27	4.60			1090	1030	1500	1410	1410					
EE19/19.8	19.10±0.40	19.84±0.30	5.00±0.25	14.50±0.40	4.55±0.20	15.14±0.30	Fig.1	2.07	47.5	23.0	1092.50	5.45	1100		1140	1060	1450	1350	1350					
EE19/20.3	19.10±0.40	20.30±0.30	5.00±0.25	14.50±0.40	4.55±0.20	15.60±0.30	Fig.1	2.10	48.4	23.0	1113.20	5.60	1100		1140	1060	1450	1350	1350					
EE19/27	20.00±0.30	27.40±0.30	5.00±0.20	14.30min	4.55±0.25	22.30±0.50	Fig.1	2.52	62.2	24.7	1536.34	7.50	950	950	950	880	1300	1200	1200	1820	2280			
EE19/27B	20.00±0.30	27.40±0.30	4.80±0.20	14.30min	4.55±0.15	22.30±0.30	Fig.1	2.61	62.2	23.8	1480.36	7.42	870	950	950	880	1250	1120	1120					
EE19/27C	20.00±0.30	27.40±0.30	4.10±0.20	14.30min	4.55±0.15	22.30±0.30	Fig.1	3.06	62.2	20.3	1262.66	6.30	710	740	740	690	1000	930	930					
EE19/27E	20.00±0.30	27.90±0.30	5.00±0.20	14.30min	4.55±0.15	22.80±0.30	Fig.1	2.56	63.2	24.7	1561.04	7.60	950		930	870	1200	1120	1120					
EE20/18.2	20.00±0.80-0.50	18.20±0.40	9.60±0.20	14.10min	5.70±0.20	12.60±0.40	Fig.1	0.811	43.0	53.0	2279.00	11.55	2600		2680	2520	3340	3140	3140					
EE21/28	20.50±0.40	27.80±0.40	6.35±0.20	14.35±0.25	6.35±0.20	21.40±0.40	Fig.1	1.52	60.7	39.9	2421.93	12.00	1480	1540	1540	1440	2000	1860	1860					
EE21/28A	20.50±0.40	27.80±0.40	6.65±0.20	14.35±0.25	6.35±0.20	21.40±0.40	Fig.1	1.45	60.7	41.8	2537.26	12.60	1550		1600	1490	2100	1950	1950					
EE22/19	22.00±0.40	18.40±0.40	5.70±0.30	15.60min	5.75±0.25	10.80±0.40	Fig.1	1.16	42.0	36.3	1524.60	8.00	1930	1930	1930	1810	2300	2160	2160	3340	3900			
EE22/19A	22.00±0.40	19.00±0.40	5.70±0.30	15.60min	5.75±0.25	11.40±0.40	Fig.1	1.19	43.2	36.2	1563.84	8.36	1930	2010	2010	1870	2500	2330	2330	3500	4600			
EE22/19B	22.00±0.40	19.30±0.30	5.20±0.20	16.00±0.40	6.00±0.25	11.00±0.20	Fig.1	1.16	42.0	36.3	1524.60	7.80	1850		1860	1740	2300	2160	2160					
EE22/29	22.00±0.40	29.80±0.40	5.75±0.25	15.60min	5.75±0.25	21.80±0.40	Fig.1	1.79	64.0	35.8	2288.13	11.50	1250		1300	1210	1700	1580	1580					
EE22/29A	22.00±0.40	29.00±0.50	5.80±0.20	16.00±0.40	5.80±0.20	21.00±0.40	Fig.1	1.75	62.3	35.7	2224.11	11.50	1320		1400	1300	1700	1580	1580					
EE22/30	22.00±0.40	30.00±0.50	5.80±0.20	16.00±0.40	5.80±0.20	22.00±0.40	Fig.1	1.79	63.9	35.7	2281.23	12.00	1290	1340	1340	1250	1700	1580	1580	2520				
EE22/30A	22.00±0.40	30.00±0.50	4.35±0.20	16.00±0.40	5.80±0.20	22.00±0.40	Fig.1	2.43	64.3	26.5	1703.95	8.85			1020	940	1300	1210	1210					
EE22/44	22.40±0.40	44.40±0.60	4.70±0.20	16.00±0.30	5.80±0.20	36.40±0.40	Fig.1	3.15	93.2	29.6	2758.72	14.00	820	850	850	780	1100	1010	1010					
EE23/18A	23.00±0.40	17.95±0.25	9.15±0.20	16.50±0.40	6.50±0.20	11.20±0.30	Fig.1	0.710	42.8	60.3	2580.84	13.20		3400	3400	3170	4300	4000	4000					
EE23/18.4A	23.00±0.40	18.35±0.25	9.15±0.20	16.50±0.40	6.50±0.20	11.60±0.30	Fig.1	0.723	43.6	60.3	2629.08	13.40			3350	3120	4250	3950	3950					
EE25/18	25.00±0.30-0.50	18.00±0-0.50	10.50±0-0.40	17.00min	7.80±0.20	10.00±0-0.50	Fig.1	0.514	41.3	80.4	3320.52	17.20	4050	4220	4200	3940	5200	4880	4880					
EE25/19	25.40±0.50	19.80±0.40	6.35±0.30	19.00±0.40	6.35±0.25	13.40±0.40	Fig.1	1.19	48.0	40.4	1939.20	9.80	1750	1850	1850	1730	2400	2240	2240	3410	4400			
EE25/19B	25.40±0.50	19.80±0.40	6.35±0.30	19.40min	6.35±0.25	13.40±0.40	Fig.2	1.19	48.0	40.4	1939.20	9.80	1750		1900	1780	2400	2240	2240					
EE25/19C	25.40±0.50	19.80±0.40	6.70±0.25	19.00±0.40	6.35±0.25		Fig.1	1.16	49.5	42.8	2118.60	10.30	1790	1860	1900	1780	2400	2240	2240					

EE 型磁芯
EE CORES




Fig.1




Fig.2




Fig. 3




Fig.4

規格 (Type)	尺寸(Unit : mm)						圖形	磁芯參數				單重 (g/Set)	Al-value (nH/N ²)										
	A	B	C	D	E	F		C1 (mm ³)	Le (mm)	Ae (mm ²)	Ve (mm ³)		KP40	KP44	KP44L	KP50	KP95	KP96	KP97	KA50	KA70	KA100	KA120
EE25/19E	25.40±0.50	19.80±0.40	9.30±0.25	19.00±0.40	6.35±0.20	13.40±0.40	Fig.1	0.833	49.5	59.4	2940.30	14.90	2430	2540	2700	2530	3400	3180	3180				
EE25/19H	25.40±0.50	19.80±0.40	15.00±0.30	19.00±0.40	6.35±0.25	13.40±0.40	Fig.1	0.517	49.5	95.8	4742.10	24.00	3290		4400	4120	5500	5150	5150				
EE25/20	25.40±0.40	20.00±0.40	6.55±0.30	18.30min	6.35±0.30	13.60±0.30	Fig.1	1.16	49.6	42.6	2112.96	10.60	1900		1900	1780	2400	2250	2250				
EE25/20A	25.40±0.40	19.95±0.40	6.35±0.25	18.70min	6.35±0.25	13.60±0.30	Fig.1	1.23	49.8	40.4	2011.92	10.00	1750	1830	1800	1690	2300	2150	2150				
EE25/32	25.40±0.50	31.80±0.60	6.35±0.25	19.00±0.40	6.35±0.30	25.40±0.60	Fig.1	1.83	73.0	40.0	2920.00	14.70	1200	1250	1250	1170	1700	1580	1580	2580	3200		
EE25/32A	25.40±0.50	31.80±0.60	6.75±0.25	19.00±0.40	6.35±0.30	25.40±0.60	Fig.1	1.71	73.5	43.1	3167.85	15.80	1270		1400	1300	1900	1760	1760				
EE25/32.6	25.40±0.50	32.60±0.40	6.35±0.25	19.00±0.40	6.35±0.30	26.20±0.40	Fig.1	1.88	75.1	40.0	3004.00	15.10	1200		1250	1170	1700	1580	1580				
EE26/13.9A	26.05±0.40	13.90±0.25	10.75±0.30	18.90±0.40	7.25±0.25	7.10±0.25	Fig.1	0.482	36.8	76.3	2807.84	14.45			4700	4400	5900	5520	5520				
EE26/14.2A	26.05±0.40	14.20±0.25	10.75±0.30	18.90±0.40	7.25±0.25	7.40±0.25	Fig.1	0.490	37.4	76.3	2853.62	14.65			4700	4400	5900	5520	5520				
EE28/21	28.50±0.40	20.90±0.40	10.80±0.20	20.50±0.40	7.30±0.25	13.30±0.30	Fig.2	0.624	51.7	82.9	4285.93	21.70	3680	3840	3840	3580	4600	4300	4300	6200	9000		
EE28/21A	28.00±0.50	21.40±0.30-0.20	12.00±0.30	18.60min	7.20±0.30	12.40±0.30-0.20	Fig.1	0.508	49.9	98.2	4900.18	26.00	4500		4400	4120	5600	5240	5240				
EE28/21C	28.50±0.40	20.40±0.40	10.80±0.20	20.50±0.40	7.30±0.25	12.80±0.40	Fig.2	0.617	50.7	82.2	4167.54	21.40	3700		3700	3460	4600	4300	4300				
EE28/21D	28.50±0.40	20.10±0.40	10.80±0.20	20.50±0.40	7.30±0.25	12.50±0.30	Fig.2	0.609	50.1	82.2	4118.22	20.00	3800		3700	3460	4700	4400	4400				
EE28/28	28.40±0.40	28.80±0.40	10.00±0.30	20.00min	7.20±0.30	19.80±0.40	Fig.1	0.826	65.4	79.2	5179.68	26.40	2630	2740	2740	2560	3700	3440	3440				
EE28/34	28.00±0.40	34.00±0.50	10.70±0.20	18.60min	7.20±0.20	25.00±0.50	Fig.1	0.855	74.4	87.0	6472.80	33.71	2820	2940	2940	2730	3700	3440	3440				
EE30/26B	30.60±0.50	26.40±0.60	10.70±0.30	19.50min	10.70±0.30	16.40±0.30	Fig.1	0.535	58.3	109	6354.70	33.70	4200	4350	4350	4060	5500	5140	5140				
EE30/30	30.00±0.80-0.60	31.00±0.00-0.80	7.30±0.00-0.50	20.00min	7.20±0.00-0.50	20.00±0.80-0.40	Fig.1	1.09	65.4	60.0	3924.00	22.04	1840	1920	1920	1800	2800	2610	2610	3750	4600		
EE30/30A	30.00±0.80-0.60	31.00±0.00-0.80	13.00±0.25	20.00min	7.20±0.00-0.50	20.00±0.80-0.40	Fig.1	0.606	66.7	110	7337.00	40.00	3450	3600	3600	3380	5100	4740	4740				
EE30/30C	30.00±0.80-0.60	30.60±0.40	10.50±0.30	20.00min	7.20±0.00-0.50	20.00±0.50-0.20	Fig.1	0.751	66.7	88.8	5922.96	32.30	2700	2810	2810	2640	4100	3820	3820				
EE30/43	30.60±0.40	43.00±0.60	10.65±0.30	20.60±0.35	10.65±0.30	33.00±0.60	Fig.1	0.842	91.8	109	10006.20	50.80	2800	2920	2920	2720	3900	3610	3610				

EE 型磁芯
EE CORES




Fig.1




Fig.2




Fig. 3




Fig.4

規格 (Type)	尺寸(Unit : mm)						圖形	磁芯參數				單重 (g/set)	Al-value (nH/N ²)											
	A	B	C	D	E	F		C1 (mm ³)	Le (mm)	Ae (mm ²)	Ve (mm ³)		KP40	KP44	KP44L	KP50	KP95	KP96	KP97	KA50	KA70	KA100	KA120	
EE30/43A	30.60±0.40	43.00±0.60	7.00±0.30	20.60±0.35	10.65±0.30	33.00±0.60	Fig.1	1.28	91.8	71.7	6582.06	33.20	1840		2000	1850	2600	2400	2400					
EE33/27	33.80±0.50	28.20±0.40	12.80±0.20	24.80min	9.70±0.20	19.60±0.40	Fig.1	0.598	68.2	114	7774.80	40.00	3550	3770	3770	3530	5200	4880	4880					
EE33.6/9.4	33.60±0.50	9.40±0.30	19.50±0.40	28.60±0.50	5.00±0.20	5.10±0.30	Fig.1	0.466	40.9	87.7	3586.93	18.30		4650	4650	4360	5800	5440	5440					
EE35/28	34.60±0.50	28.80±0.50	9.30±0.30	25.10min	9.40±0.25	19.60±0.50	Fig.1	0.822	69.7	84.8	5910.56	30.00	2900	3000	3000	2440	3800	3530	3530	4300	6600			
EE3528S	34.60±0.50	28.60±0.60	9.30±0.30	25.60±0.50	9.40±0.25	19.60±0.60	Fig.2	0.822	69.7	84.8	5910.56	29.00	2600		3000	2790	3800	3530	3530					
EE35/30	35.00±0.40	30.20±0.40	11.75±0.25	25.00±0.40	10.05±0.25	18.20±0.40	Fig.1	0.551	68.3	124	8469.20	44.00	4400	4590	4590	4260	5600	5210	5210	7400	10000			
EE35/30A	35.00±0.40	30.20±0.40	10.00±0.25	25.00±0.40	10.05±0.25	18.20±0.40	Fig.1	0.644	68.3	106	7239.80	37.70	3780		3800	3540	4800	4460	4460					
EE35/49	35.00±0.50	48.80±0.40	10.00±0.30	24.50min	10.00±0.30	36.60±0.40	Fig.1	1.00	104	104	10816.00	55.70	2020		2600	2410	3400	3140	3140					
EE39.5/13	39.50±0.60	12.95±0.30	13.50±0.30	34.20min	4.70±0.20	8.15±0.30	Fig.1	0.837	53.8	64.3	3459.34	17.20			2780	2600	3500	3280	3280					
EE40/35	40.10±0.70	34.80±0.40	11.70±0.20	27.50min	11.70±0.20	20.60±0.50	Fig.1	0.524	77.6	148	11484.80	59.30	4200	4500	4500	4200	5700	5310	5310					
EE41/33	41.00±0.70	34.60±0.40	12.70±0.25	29.00min	12.50±0.25	21.80±0.60	Fig.1	0.512	79.9	156	12464.40	64.00	4080	4150	4150	3900	6300	5840	5840					
EE42/15	42.00±0.60-0.40	42.50±0.40	15.00±0.25	29.50min	12.20±0.00-0.50	30.00±0.80-0.00	Fig.1	0.550	97.9	178	17426.20	88.00	4320	4510	4510	4200	6100	5640	5640					
EE42/20	42.00±1.00-0.70	42.50±0.50	19.70±0.30	29.50min	12.00±0.30	30.50±0.50	Fig.1	0.416	97.8	235	22983.00	116.00	5610	5850	5850	5450	7640	7100	7100					
EE42.4/13	42.40±0.60	12.96±0.30	13.50±0.30	37.00min	4.80±0.20	8.16±0.30	Fig.1	0.873	56.6	64.8	3667.68	18.20			2750	2570	3520	3280	3280					
EE42.4/13.2	42.40±0.60	13.20±0.30	13.50±0.30	37.00min	4.80±0.20	8.40±0.30	Fig.1	0.881	57.1	64.8	3700.08	18.36			2730	2550	3500	3250	3250					
EE44/12.6	44.00±0.75	12.60±0.30	20.00±0.35	38.40±0.75	5.50±0.20	7.80±0.30	Fig.4	0.564	56.4	100.0	5640.00	30.50			4600	4200	5900	5500	5500					
EE50.5/53.8A	50.50±0.80	53.80±0.40	11.00±0.30	33.90min	16.00±0.25	37.80±0.40	Fig.1	0.713	119	167	19873.00	106.50			3840	3560	5000	4620	4620					
EE55/55	55.15±1.05	55.00±0.60	21.00±0.00-0.80	37.50min	16.95±0.25	37.60±0.60	Fig.1	0.348	123	353	43419.00	218.20	7400	7600	7600	7050	10000	9240	9240					
EE55/55A	55.15±1.05	55.00±0.60	24.70±0.30	37.50min	16.95±0.25	37.60±0.60	Fig.1	0.291	123	422	51906.00	268.00	7400	7700	7700	7210	12000	11060	11060					
EE55/55B	55.15±1.05	55.00±0.60	12.50±0.30	37.50min	16.95±0.25	37.60±0.60	Fig.1	0.574	123	214	26358.90	135.64	4500		4600	4260	6100	5620	5620					